

Technical Data Sheet

FLUTING S
Recycled

PM -- 1

Properties	Units	Test method														
Basis weight	g/m ²	ISO 536	100	105	110	120	130	135	140	145	150	170				
Basis weight tolerance			±5%													
SCT _{CD}	Typical	ISO 9895	1,85	1,95	2,05	2,20	2,35	2,50	2,55	2,65	2,75	2,80				
	Min		1,70	1,80	1,90	2,05	2,20	2,30	2,35	2,45	2,55	2,60				
CMT ₃₀	Typical		160	170	180	200	215	220	230	240	250	255				
	Min		150	160	165	185	200	205	215	220	230	235				
Moisture	%	ISO 287	7 ± 1													
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)																
Valid from 01.01.2021. onwards																

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.

Rev/Date 01.01.2021.	PREPARED BY  HEAD OF QUALITY CONTROL AND CENTRAL LABORATORY	COORDINATED BY  PRODUCTION MANAGER	APPROVED BY  EXECUTIVE DIRECTOR
-------------------------	---	---	--