

Technical Data Sheet		PM - 1										
<b>FLUTING Recycled</b>												
Properties	Units	Test method										
Basis weight	g/m <sup>2</sup>	ISO 536	100	105	110	120	125	130	140	145	150	170
Basis weight tolerance			±5%									
SCT <sub>CD</sub>	Typical	ISO 9895	1,60	1,65	1,80	1,85	1,90	2,00	2,05	2,10	2,15	2,20
	Min		1,50	1,55	1,70	1,75	1,80	1,85	1,90	1,95	2,00	2,10
CMT <sub>30</sub>	Typical	ISO 7236	155	160	175	190	200	205	210	215	220	230
	Min		145	150	165	175	185	190	195	200	205	215
Moisture	%	ISO 287	7 ± 1									
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C ( ISO 187 )												
Valid from 01.01.2021. onwards												

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.

Rev/Date 01.01.2021.	PREPARED BY  HEAD OF QUALITY CONTROL AND CENTRAL LABORATORY	COORDINATED BY  PRODUCTION MANAGER	APPROVED BY  EXECUTIVE DIRECTOR
-------------------------	--	--	---------------------------------------