

Technical Data Sheet		PM - 1										
<b>SCHRENZ Recycled</b>												
Properties	Units	Test method										
Basis weight	g/m <sup>2</sup>	ISO 536	90	100	110	120	130	135	140	150	180	
Basis weight tolerance			±5%									
Bursting Strength	kPa	ISO 2758	Min 155	160	180	190	200	205	210	215	250	
Burst Index	kPam <sup>2</sup> /g	ISO 2758	Min 1,7	1,6	1,6	1,6	1,5	1,5	1,5	1,4	1,4	
Moisture	%	ISO 287	7 ± 1									
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C ( ISO 187 )												
Valid from 25.02.2021. onwards												

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.

Rev/Date 25.02.2021.	PREPARED BY  HEAD OF QUALITY CONTROL AND/CENTRAL LABORATORY	COORDINATED BY  PRODUCTION MANAGER	APPROVED BY  EXECUTIVE DIRECTOR
-------------------------	---	--	--