

Technical Data Sheet		PM – 1										
TESTLINER 3 Recycled												
Properties	Units	Test method										
Basis weight	g/m ²	ISO 536	110	115	120	125	130	135	140	140	170	
Basis weight tolerance			±5%									
SCT _{CD}		Typical	1,60	1,70	1,80	1,90	1,95	2,00	2,05	2,05	2,35	
		Min	1,50	1,55	1,60	1,65	1,70	1,75	1,80	1,80	2,10	
Bursting Strength		Typical	250	275	285	290	305	310	330	330	360	
		Min	240	250	270	280	290	300	310	310	350	
Cobb ₆₀ (top)	g/m ²	ISO 535	< 50									
Moisture	%	ISO 287	7 ± 1									
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187) Valid from 25.02.2021. onwards												

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions

Rev/Date 25.02.2021.	PREPARED BY  HEAD OF QUALITY CONTROL AND CENTRAL LABORATORY	COORDINATED BY  PRODUCTION MANAGER	APPROVED BY  EXECUTIVE DIRECTOR
-------------------------	---	--	--