



Technical Data Sheet

SINGLE WALL CORRUGATED BOARD

Corrugated board	Grade	Paper grades	Flute	Basis weight g/m ²	BST (min) kPa ISO 2759	PET (min) J ISO 3036	ECT (min) kN/m ISO 3037
Single wall	2Š	S-WL-S 90-100-90	C	330	480	2,4	2,8
			B		440	2,4	2,8
			E		400	-	-
		S-WL-S 100-100-100	C	350	500	2,6	3,0
			B		460	2,6	3,0
			E		420	-	-
		S-WL-S 100-110-100	C	360	520	2,8	3,2
			B		480	2,8	3,2
			E		440	-	-
	TŠ	TL3-WL-S 115-110-110	C	385	540	3,0	3,4
			B		500	3,0	3,4
			E		460	-	-
		TL3-WL-S 115-110-100	C	375	520	2,8	3,2
			B		480	2,8	3,2
			E		440	-	-
TL3-WL-S 115-100-100	C	365	500	2,6	3,0		
	B		460	2,6	3,0		
	E		420	-	-		
2T	TL3-WL-TL3 115-120-115	C	410	560	3,2	3,6	
		B		520	3,2	3,6	
		E		480	-	-	
	TL3-WL-TL3 115-110-115	C	400	540	3,0	3,4	
		B		500	3,0	3,4	
		E		460	-	-	
TL3-WL-TL3 115-100-115	C	390	520	2,8	3,2		
	B		480	2,8	3,2		
	E		440	-	-		

Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)

NOTE : Listed basis weight of corrugated board are teoretical and they can be used only for orientation.



Technical Data Sheet

SINGLE WALL CORRUGATED BOARD

Corrugated board	Grade	Paper grades	Flute	Basis weight g/m ²	BST (min) kPa ISO 2759	PET (min) J ISO 3036	ECT (min) kN/m ISO 3037
Single wall	BT	BTL-WL-TL3 125-120-115	C	425	540	3,2	3,4
			B		500	3,2	3,4
			E		460	-	-
		BTL-WL-TL3 125-110-115	C	405	500	3,0	3,3
			B		480	3,0	3,3
			E		440	-	-
	BTL-WL-TL3 125-100-115	C	395	540	2,8	3,2	
		B		500	2,8	3,2	
		E		460	-	-	
	BŠ	BTL-WL-S 125-120-110	C	410	500	2,8	3,2
			B		480	2,8	3,2
			E		420	-	-
BTL-WL-S 125-110-110		C	400	490	2,7	3,1	
		B		450	2,7	3,1	
		E		410	-	-	
BTL-WL-S 125-100-110	C	390	480	2,6	3,0		
	B		440	2,6	3,0		
	E		400	-	-		

Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)

NOTE : Listed basis weight of corrugated board are teoretical and they can be used only for orientation.