



Technical Data Sheet													PM – 1		
<b>FLUTING S</b> Recycled															
Properties	Units	Test method													
Basis weight	g/m <sup>2</sup>	ISO 536		100	105	110	120	130	135	140	145	150	160	170	
Basis weight tolerance				±5%											
SCT <sub>CD</sub>	kN/m	ISO 9895	Typical	1,85	1,95	2,05	2,20	2,35	2,50	2,55	2,65	2,75	2,78	2,80	
			Min	1,70	1,80	1,90	2,05	2,20	2,30	2,35	2,45	2,55	2,58	2,60	
CMT <sub>30</sub>	N	ISO 7236	Typical	160	170	180	200	215	220	230	240	250	253	255	
			Min	150	160	165	185	200	205	215	220	230	233	235	
Moisture	%	ISO 287	7 ± 1												
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C ( ISO 187 ) Valid from 01.01.2022. onwards															

**Comments :** Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.