



Technical Data Sheet												PM – 1	
FLUTING Recycled													
Properties	Units	Test method											
Basis weight	g/m ²	ISO 536		100	105	110	120	125	130	140	145	150	170
Basis weight tolerance				±5%									
SCT _{CD}	kN/m	ISO 9895	Typical	1,60	1,65	1,80	1,85	1,90	2,00	2,05	2,10	2,15	2,20
			Min	1,50	1,55	1,70	1,75	1,80	1,85	1,90	1,95	2,00	2,10
CMT ₃₀	N	ISO 7236	Typical	155	160	175	190	200	205	210	215	220	230
			Min	145	150	165	175	185	190	195	200	205	215
Moisture	%	ISO 287	7 ± 1										
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187) Valid from 01.01.2022. onwards													

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.