



Technical Data Sheet								PM – 1		
NH MIX Kraft Paper										
Properties	Units	Test method	Typical values							
Basis weight	g/m ²	ISO 536	70	80	90	100	110	115	120	
Basis weight tolerance			±5%	±5%	±5%	±5%	±5%	±5%	±5%	
Tensile Strength	kN/m	ISO 1924-3	md	6,7	7,6	8,6	9,5	10,4	10,9	11,4
			cd	2,8	3,2	3,6	4,0	4,0	4,1	4,2
Tear	mN	ISO 1974	md	525	600	675	750	825	863	1020
			cd	595	680	765	850	935	978	1140
Cobb ₆₀	g/m ²	ISO 535	30							
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)										
Valid from 01.01.2022. onwards										

The table above shows typical values