



Technical Data Sheet											PM – 1			
SCHRENZ														
Recycled														
Properties	Units	Test method												
Basis weight	g/m ²	ISO 536		90	100	110	120	130	135	140	150	180	200	
Basis weight tolerance				±5%										
Bursting Strength	kPa	ISO 2758	Min	155	160	180	190	200	205	210	215	250	280	
Burst Index	kPam ² /g	ISO 2758	Min	1,7	1,6	1,6	1,6	1,5	1,5	1,5	1,4	1,4	1,4	
Moisture	%	ISO 287		7 ± 1										
Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)														
Valid from 01.01.2022. onwards														

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.