



Technical Data Sheet

PM – 1

TESTLINER ONE LAYER
Recycled

Properties	Units	Test method										
Basis weight	g/m ²	ISO 536		110	115	120	125	130	135	140	170	200
Basis weight tolerance				±5%								
SCT _{CD}	kN/m	ISO 9895	Typical	1,60	1,70	1,80	1,90	1,95	2,00	2,05	2,35	2,65
			Min	1,50	1,55	1,60	1,65	1,70	1,75	1,80	2,10	2,40
Bursting Strength	kPa	ISO 2758	Typical	250	275	285	290	305	310	330	360	370
			Min	240	250	270	280	290	300	310	350	360
Cobb ₆₀ (top)	g/m ²	ISO 535	< 50									
Moisture	%	ISO 287	7 ± 1									

Test conditions : RH 50 ± 2%; temperature 23 ± 1°C (ISO 187)
Valid from 01.01.2022. onwards

Comments : Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions