



Technical Data Sheet

PM - 4

NH SK – Standard Sack Kraft Paper

Properties	Units	Test method		Typical values				
Basis weight	g/m ²	ISO 536		70	75	80	85	90
Basis weight tolerance				± 3%				
Tensile Strength	kN/m	ISO 1924-3	MD	6,3	6,7	7,2	7,6	8,1
			CD	3,9	4,1	4,4	4,7	4,9
Tensile Index	Nm/g	ISO 1924-3	MD	90	90	90	90	90
			CD	55	55	55	55	55
Stretch	%	ISO 1924-3	MD	2,5	2,5	2,5	2,5	2,5
			CD	7,0	7,0	7,0	7,0	7,0
TEA	J/m ²	ISO 1924-3	MD	105	112	120	128	135
			CD	180	195	205	220	230
TEA Index	J/g	ISO 1924-3	MD	1,5	1,5	1,5	1,5	1,5
			CD	2,6	2,6	2,6	2,6	2,6
Tear Index	mNm ² /g	ISO 1974	MD	10,5	10,5	10,5	10,5	11
			CD	11,5	11,5	11,5	11,5	12
Cobb ₆₀	g/m ²	ISO 535		32	32	32	32	32
Gurley	s	ISO 5636/5		25	25	25	25	25

Test conditions : 50 ± 2% RH; 23 ± 1°C (ISO 187)

Valid from 01.01.2022. onwards

The table above shows typical values

Comments :

Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions. Different TEA and stretch is possible within certain limits if so required by the customer .

NH Standard Sack Kraft is also available in wet strength quality (min average of value in both MD and CD is 15%)